



**Technical Data Sheet
Carboxylated Nitrile 70A Black**

| Property | Rating or Value |
|---------------------------------|------------------------|
| Tensile, PSI | 2256 |
| Modulus, 300% | 2270 |
| Tear Strength, PSI | 231 |
| Hardness, Shore A | 70 |
| Elongation, % | 290 |
| Specific Gravity | 1.18 |
| Chemical Resistance | Excellent |
| Max Service Temperature (deg F) | 275 |

Above values are typical and to be used as a guide only. They are not intended to be used for engineering specifications. End user must test in their application to determine suitability.