



**Technical Data Sheet
Millable Urethane 70A Black**

Property	Rating or Value
Tensile, PSI	2582
Modulus, 100%	1897
Tear Strength, PSI	173
Hardness, Shore A	70
Elongation, %	125
Chemical Resistance	Good
Max Service Temperature (deg F)	212

Above values are typical and to be used as a guide only. They are not intended to be used for engineering specifications. End user must test in their application to determine suitability.